

# A Waterbase Below Grade Elastomeric Seamless Waterproofing Membrane.

GREEN FRIENDLY PRODUCTS!

## DESCRIPTION & USE

BG 2000 is a unique Acrylic Waterbased coating which forms an elastomeric waterproofing membrane with excellent bonding characteristics to most building materials. Specifically designed for BELOW GRADE AND UNDERLAYMENT applications.

## ADVANTAGES

- Low Cost - Minimum Down Time
- Ease of Application
- Superior Waterproofing
- Excellent Bond Strength
- High Tensile Strength and Elastomeric Properties
- Freeze-Thaw Resistant
- Waterbased - Environmentally Safe to Use and Apply

## SEE TEST DATA

## SURFACE PREPARATION

Substrate must be structurally sound and free from grease, oil, dirt, dust, sealers, water repellents and other foreign materials which may interfere with proper bonding. Shot blasting, sand blasting, or water sand blasting with minimum 3500 psi may be necessary over some surfaces to achieve proper bonding. On concrete block or slumpstone walls, all head and bed joints must be free of holes and finished flush with block substrate. For poured in place walls, a waterbase form release must be used. If an oil base release is used, it can be completely removed with trisodium phosphate (TSP), power washed and rinsed.

## APPLICATION

Spray one (1) heavy coat or roll two (2) coats of MULASTICOAT® BG 2000 over area to be waterproofed at a coverage rate of 35-45 sq. ft. per gallon. Allow to dry, then backfill. Always use a drainage system at bottom of footing of retaining wall. MULTICOAT'S LASTO DRAIN or equivalent is recommended.

**FOR BELOW GRADE AND UNDERLAYMENT WATERPROOFING USE ONLY**

## LIMITATIONS

Do not apply if substrate temperature is below 40°F and falling, above 100°F and rising, or if precipitation is expected within a twenty four (24) hour period after each coat.

**Do not use if substrate is subject to negative side water or water vapor pressure.**

## COVERAGE

35-45 sq. ft. per gallon, one coat. (Coverage may vary due to application method and/or substrate condition.)



5 GALLON BUCKET

55 GALLON DRUM



275 GALLON TOTE

ENVIRONMENTALLY SAFE, WATERBASE AVAILABLE IN 5 GALLON BUCKETS, 55 GALLON DRUMS & 275 GALLON TOTES



BG 2000 CAN BE APPLIED BY SPRAYER, HOPPER GUN, ROLLER OR BRUSH



READY FOR BACKFILL

**BG 2000**  
Below Grade Waterproofing



## PACKAGING AND STORAGE

Furnished in 5 gallon pails, 55 gallon drums, and 275 gallon totes. Store at 40-90°F. Shelf life is approximately 18 months in unopened containers.

## LIMITATIONS

Do not apply if substrate temperature is below 40°F or above 100°F, or if ambient temperature below 40°F above 100°F.

Do not apply if precipitation is expected within a twenty four (24) hour period.

## DAMAGE LIMITATION

Seller shall not be liable for any damages, injury, loss, direct or consequential, resulting from its products. The parties intend that the limitation of damages, including consequential damages, applies even if the exclusive remedy provided for herein fails of its essential purpose.

## EXCLUSIVE REMEDY

Seller's sole obligation, and buyer's exclusive remedy shall be to replace material if found to be defective.

## WARRANTY DISCLAIMER

There are no warranties which extend beyond the description of the fact hereof. Seller expressly disclaims all other warranties regarding the use of its products, whether expressed or implied, including the implied warranties of merchantability and for fitness of a particular purpose. Since use of the product is beyond the Seller's control, the Buyer assumes all risk of use.

## WARRANTY

Materials are guaranteed with respect to uniformity and quality within manufacturer's specifications.

## TEST DATA - BG 2000 BELOW GRADE WATERPROOFING

TEST	METHOD	BG 2000 RESULTS
Tensile Bond Adhesion to Concrete	ASTM C297	335 psi (coh/adh)
Tensile Strength	ASTM D 412	399 psi
Elongation	ASTM D412	319.3%
Hydrostatic Head	12" Water/Film @ 40mil	Pass 96 Hrs/no effect
Hydro. Pressure	ASTM C1306	Pass >45 psi <sup>1</sup>

<sup>1</sup> The test procedure only calls for taking the pressure to 45 psi but after passing so easily, test was taken up to 80 psi for 3 hours and surface still did not leak.



### MULTICOAT® CORPORATION West Coast

Toll Free: (877) 685-8426  
(949) 888-7100 Fax (949) 888-2555  
Website: [www.multicoat.com](http://www.multicoat.com)  
E-mail: [info@multicoat.com](mailto:info@multicoat.com)

### MULTICOAT® PRODUCTS, INC. East Coast

Toll Free: (800) 660-6729  
(304) 586-0616 Fax (304) 586-0620  
Website: [www.multicoat.com](http://www.multicoat.com)  
E-mail: [info@multicoat.com](mailto:info@multicoat.com)

AVAILABLE THROUGH

MC311

*The Coating of the Future... Today*