



## Sticky Seal **FLEX-C**

### Adhesive Sealant Caulking

#### Product Description

Flex-C is a high performance joint sealant for a wide range of construction applications. Flex-C delivers tough, elastic sealing performance, for joints requiring compression and extension greater than 35%.

#### Product Information: Features & Benefits

- Solvent and isocyanate free, 100% solids
- Non-silicone
- Non-flammable
- Fast-curing
- Primerless bonding to most surfaces
- Paint compatible
- Low odor
- Extremely low shrinkage
- Non-staining
- Mildew resistant

#### Standards & Compliance

- May contribute to LEED V4 EQ Material Resource Credit 4.1 - Adhesives and Sealants
- ASTM C920, Type S, Grade NS, Class 35  
 Uses NT, T, G, A & O
- Federal Specification TT-S-00230-C Type II, Class B
- Corps of Engineers CRD-C-541, Type II, Class B
- Conforms to OTC Rule for Sealants and Caulks
- Meets requirements of California Regs: CARB, BAAQMD and SCAQMD
- Conforms to USDA Requirements for Non-food Contact

#### Common Applications

- Roofing
- Parapets
- Window and door frames
- Block and Masonry
- Expansion Joints
- Siding
- Weather Sealing
- Cove Joints

#### High Performance Durability

- Flex-C can be installed on damp surfaces which is defined as when no moisture is transferred to the skin when the substrate is touched
- The cured bead exhibits excellent long-term adhesion to the porous surfaces
- Does not dry or become brittle

#### Typical Properties

Please contact your Multicoat Sales Representative before writing specifications around this product. Product properties are as follows:

Property	Typical Value	Units	Test Method
VOC's	34.5 g/L		EPA Test Method 24
Skinover time (50% RH 70°F)	30	Min	Min. ASTM C679
Density	12.7	#/gal	
Hardness	50	Shore A	
Shear Strength	185.7	psi	ASTM D1002
Peel Strength	12.7 25.1 25.7 26.7 24.0 25.8 23.9	lbf/in.	ASTM D903
Tensile	268	psi	ASTM D412
Elongation at Break	259	%	ASTM D412
Chemistry	Hybrid Polymer		
Movement	+/- 35%		ASTM C920
Shrinkage	0%		
Service Temperature	-40°F - 200°F		
Viscosity	2,730,000 1,555,000 460,000	cps @ 1 rpm cps @ 2 rpm cps @ 10 rpm	ASTM D2196-10

Flex-C typical values represent data from multiple batches. Values will be refreshed, as necessary, upon data collection from additional campaigns and long-term variability discernment.



## Flex-C

### Application

Remove all dirt, oil, loose paint, frost and other contamination from all working surfaces. Maintain Flex-C at room temperature before applying to ensure easy gunning and tooling. Test and evaluate to ensure adequate adhesion. Carefully gun the sealant with a smooth, continuous bead. If tooling is needed, do so within fifteen minutes of application.

### Concrete

Prior to application remove any residual contamination by mechanical abrasion, sand blasting or power washing. On green concrete, remove all release agents and loose concrete. Dry all visible and/or standing water. Install an appropriate backer rod to avoid three-point bonding.

### Metal

Prepare all metal to ensure maximum adhesion. Remove all rust, scale and residue using a wire brush. Remove films, loose or inappropriate coatings and oils with an appropriate solvent such as alcohol.

\*Multicoat recommends that coated substrates be tested for proper adhesion prior to starting a project to determine suitability for use.

### Wood

Wood should be clean, sound and dry prior to sealant application. Allow treated wood to weather for six months prior to application. Remove all coatings and paint to ensure proper adhesion. Flex-C is not recommended for use on fire retardant lumber.

### Priming

In most applications Flex-C will not require a primer. However, certain substrates may require a primer to ensure a long lasting bond and weatherproof seal. It is the applicator's responsibility to determine whether or not a primer is needed in their specific application.

### Clean-up

Clean tools and any uncured adhesive with mild solvent such as mineral spirits.

### Material Storage/Disposal

Store securely between 60° F - 80° F in unopened container. Recommended shelf life is 12 months from date of manufacture on bottom of tube. Keep tube tightly sealed. Dispose of contents/container in accordance with Local/Regional/National/International Regulations. Refer to Safety Data Sheet (SDS) for further information.

### Shelf Life and Storage

The shelf life is 12 months for an unopened container from the date of manufacture. Reference the date of manufacture. YYMMDD ex. 190522 is May 22, 2019.

### Colors



Limestone

### Packaging

- 10.3 oz Caulking Tubes
- 20 oz Sausages

### Warranty

Multicoat warrants that our products are manufactured and conform to strict quality assurance specifications. For warranty information visit: <https://multicoat.com/warranties/>

### Limitations

Flex-C should not be used in applications in which it will be permanently exposed to liquid water.

### Precautionary Statements

Do not use until all instructions and safety precautions have been read and understood. Wear protective gloves, protective clothing and eye protection. Wash contaminated clothing before reuse. Contaminated work clothing should not be allowed out of the workplace.

IF ON SKIN: Wash exposed body areas with soap and water.

IF IN EYES: Rinse with water, remove contact lenses and continue rinsing. If exposed or concerned get medical advice/attention. Refer to Safety Data Sheet (SDS) for further information.